

# MARKCHEM SUPFLOOR 100

HIGH ABRASION, MONOLITHIC DRY SHAKE FLOOR HARDENER



## DESCRIPTION

**SUPFLOR 100** is a pre-mixed powder designed to be applied as a dry shake over freshly floated concrete floor. It contains special hardwearing aggregates, which have been selected for their physical properties of high abrasion and wear resistance. It cures monolithically to provide a dense, non-porous surface, which is extremely hardwearing and abrasion resistant. Monolithic cure ensures that problems normally associated with these screeds e.g. shrinkage cracking, curing etc. are completely overcome.

## FEATURES / ADVANTAGES

- High abrasion resistant floor hardener giving a maintenance free floor
- A bond monolithically to the base concrete and ensures a hard wearing surface
- Hard dense surface resist to oil and greases
- Easy and economical to apply
- Non-Rusting

## TYPICAL APPLICATIONS

- For areas subjected to heavy wear and tear
- Used on areas subjected to heaviest traffic like loading bays, workshops, commercial floors
- Warehouses and Storerooms
- Steel industries, power station, agricultural buildings, distillation plants, laboratories

# MARKCHEM SUPFLOOR 100

HIGH ABRASION, MONOLITHIC DRY SHAKE FLOOR HARDENER



## TYPICAL CHARACTERISTICS

- Nature/Appearance : Single component powder
- Color : Grey
- Hardness : 7-8 Moh's Scale
- Adhesion to Concrete : Monolithic

## SPECIFICATION COMPLIES

- IS 1237 – 1980

## DIRECTIONS FOR USE

### METHOD FOR USAGE

- Concrete mix should be designed to minimize segregation and bleeding. The base concrete should have minimum cement content of 300 kg/ m<sup>3</sup> OR M-20 Grade of concrete.
- Water: Cement ratio should be always less than 0.54. Slump should be 70 to 100 mm.
- If required use water reducing agent MarkPlast HSP-30. Application of Supflor 100 should begin without delay when the base concrete has stiffened. It is recommended that the floor be marked off into bays of known area. Sufficient material then lay out to meet the required spread rates. This is applied in two application states
- (The first application is made by using 1/2 to 2/3 of the material required for eventual and use). This is evenly broad caste on to the concrete surface. When the material becomes uniformly dark by the absorption of moisture from the concrete this application can be floated. Wooden floats or on large areas, the power trowel with disc may be used. However that the surface is not overworked
- Immediately after floating the remaining materials is thrown evenly over the surface. Again moisture is absorbed and the surface can be floated in the same way as before

# MARKCHEM SUPFLOOR 100

HIGH ABRASION, MONOLITHIC DRY SHAKE FLOOR HARDENER



- Final finishing of the floor using the power trowel with blades can be carried out when the floor has stiffened so that damage will not be caused.
- Proper curing practices should be adopted after application.

## COVERAGE

Application rate kg/sq. m	Intended traffic use
3	<b>Light</b>
4	<b>Medium</b>
5	<b>Heavy</b>

## CLEANING OF TOOLS

Tools and equipment can be easily cleaned with water. Skin contact should be avoided as it is slightly acidic & seek medical advice.

## STORAGE AND SHELF LIFE

Store the material in cool and dry place (25<sup>0</sup>C temp). Shelf life is one year when materials are stored in unopened containers as per recommended storage conditions.

## PACKING

25 Kg Bag

## PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

## DISCLAIMER

The above information and details herein are based on the tests conducted & experience on application and usage. The user is advised to carry out the test and take trials to satisfy on the suitability of the products and meeting his requirement considering the prevailing conditions prior to apply/ using it on larger area. As the conditions under which the products are used or transported are beyond our control. We would not hold ourselves responsible on its consequential nonperformance.